## TECHNICAL FEATURES

| | |
|---|---|
| **Trade Name** | Clamps for glass joints |
| **Use** | For safe connection of standard-finish glass conical joints |
| **Material** | POM |
| **Other features** | Colour : Green |

## DIMENSIONAL SPECIFICATIONS

| | |
|---|---|
| **Useful range diameter** | 10/19 |



## GENERAL FEATURES

| | |
|---|---|
| **CE mark** | No |
| **Foodstuff suitability** | n.a. |

## STERILIZATION

| | |
|---|---|
| **Autoclavability at +121°C** | Yes |
| **Gas (Ethylene Oxide)** | Yes |
| **Dry at 160°C** | Yes |
| **Chemical (Formalin)** | Yes |
| **Radiations** | No |
| **Microwave** | No |

## CLEANING OPERATIONS

| | |
|---|---|
| **Slight contamination** | Wash with neutral detergent (pH 7) |
| **Consistent contamination** | Wash with alkaline detergent (pH up to 12) |

**Quality Assurance**

This paper is an electronic print-out: signature is not requested

## CHEMICAL RESISTANCES

| Categories of substances | Reference | Concentration % | T. 20° C | T. 40° C | T. 60° C |
|---|---|---|---|---|---|
| **Inorganic Acid** | Sulphuric acid | 98 | C | - | - |
| **Organic Acid** | Benzoic acid | 100 | B | B | C |
| **Alcohol** | Ethanol | 100 | A | B | B |
| **Aldehydes** | Acetaldeyde | 100 | A | A | A |
| **Inorganic alkali** | Isodium hydroxide | 50 | C | - | - |
| **Organic alkali** | Aniline | 100 | A | B | C |
| **Ketone** | Acetone | 100 | - | - | - |
| **Esther** | Ethyl acetate | 100 | B | C | - |
| **Hydrocarbons, halogenated** | Dichloroethylene | 100 | C | - | - |
| **Hydrocarbons, aromatic** | Benzene | 100 | A | B | C |
| **Hydrocarbons, linear** | Hexane | 100 | A | A | A |
| **Supersolvent** | Tetrahydrofuran | 100 | A | B | B |

**Legenda** (not applicable if neglected)**:**

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damages.

**Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.**

Information about resistance of plastic materials to temperatures, sterilization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products

## PACKAGING

| | |
|---|---|
| **Bag** | 10 pcs |
| **Box** | 1000 pcs |

**Quality Assurance**

This paper is an electronic print-out: signature is not requested