MG 160

Characteristics:

Binder-free micro-glass fibre filter paper.

Applications:

Air sampling to collect atmospheric particulates and aerosols.

High volume PM-10 sampling.

Benefits:

Temperature resistant to about 500°C..

Physical properties	Method	Units	Typical value
Basis weight	ISO 536	g/m2	73
Pressure drop	Internal	Pa	560
Filtration speed	Herzberg	Ml/min	390
Penetration (0,3 µm)**	EN143	%	< 0,001

*** At 15 cm/s, paraffin oil.*

All indicated data are to be understood as typical average values.

20221019; Version 2.

Contact office:

Ahlstrom-Munksjö Falun AB
Box 1003
SE-79110 Falun
Sweden
T: +46 23 705880
E-mail: CS.Falun@ahlstrom-munksjo.com

www.ahlstrom-munksjo.com

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom-Munksjö deems appropriate. Refer to www.ahlstrom.com for contact information.

© Ahlstrom-Munksjö 2017