Sulfuric Acid 96%
Finyte®

Material No.: 5859-07
:
Revision No.: 0

Product Specification

Test	Specification
Assay (H_2SO_4)	95.0 - 97.0 %
Color (APHA)	≤ 10
Chloride (Cl)	≤ 0.1 ppm
Nitrate (NO_3)	≤ 0.1 ppm
Phosphate (PO_4)	≤ 0.20 ppm
Trace Impurities - Aluminum (Al)	≤ 10.0 ppb
Arsenic and Antimony (as As)	≤ 2.0 ppb
Trace Impurities - Barium (Ba)	≤ 5.0 ppb
Trace Impurities - Beryllium (Be)	≤ 1.0 ppb
Trace Impurities - Bismuth (Bi)	≤ 10.0 ppb
Trace Impurities - Boron (B)	≤ 10.0 ppb
Trace Impurities - Cadmium (Cd)	≤ 5.0 ppb
Trace Impurities - Calcium (Ca)	≤ 10.0 ppb
Trace Impurities - Chromium (Cr)	≤ 5.0 ppb
Trace Impurities - Cobalt (Co)	≤ 5.0 ppb
Trace Impurities - Copper (Cu)	≤ 5.0 ppb
Trace Impurities - Gallium (Ga)	≤ 10.0 ppb
Trace Impurities - Germanium (Ge)	≤ 10.0 ppb
Trace Impurities - Gold (Au)	≤ 5.0 ppb
Trace Impurities - Iron (Fe)	≤ 10.0 ppb
Trace Impurities - Lead (Pb)	≤ 10.0 ppb
Trace Impurities - Lithium (Li)	≤ 5.0 ppb
Trace Impurities - Magnesium (Mg)	≤ 10.0 ppb
Trace Impurities - Manganese (Mn)	≤ 5.0 ppb
Trace Impurities - Molybdenum (Mo)	≤ 5.0 ppb
Trace Impurities - Nickel (Ni)	≤ 5.0 ppb
Trace Impurities - Niobium (Nb)	≤ 5.0 ppb
Trace Impurities - Potassium (K)	≤ 10.0 ppb

>>> Continued on page 2 >>>

For questions on this Product Specification please contact Technical Services at 855.282.6867 or +1.610.386.1700
Avantor Performance Materials, LLC
100 Matsonford Rd, Suite 200, Radnor, PA 19087. U.S.A. Phone 610.386.1700

Material No.: 5859-07

Test	Specification
Trace Impurities - Silicon (Si)	≤ 10.0 ppb
Trace Impurities - Silver (Ag)	≤ 5.0 ppb
Trace Impurities - Sodium (Na)	≤ 10.0 ppb
Trace Impurities - Strontium (Sr)	≤ 5.0 ppb
Trace Impurities - Tantalum (Ta)	≤ 10.0 ppb
Trace Impurities - Thallium (Tl)	≤ 10.0 ppb
Trace Impurities - Tin (Sn)	≤ 10.0 ppb
Trace Impurities - Titanium (Ti)	≤ 5.0 ppb
Trace Impurities - Vanadium (V)	≤ 5.0 ppb
Trace Impurities - Zinc (Zn)	≤ 10.0 ppb
Trace Impurities - Zirconium (Zr)	≤ 10.0 ppb
Particle Count at point of fill - 0.2 µm and greater	≤ 2000 par/ml
Particle Count at point of fill - 0.5 µm and greater	≤ 150 par/ml
Particle Count at point of fill - 1.0 µm and greater	≤ 25 par/ml

>>> Continued on page 3 >>>

Material No.: 5859-07

Test	Specification

For Microelectronic Use
Storage Condition: Recommended Storage Conditions: 15° - 100°F

Packaging Site: Phillipsburg Mfg Ctr & DC