

2-Propanol  
CMOS  
(iso-propyl alcohol)



Material No.: 9059-4S  
Revision No.: 0

## Product Specification

Test	Specification
Assay (CH <sub>3</sub> CHOHCH <sub>3</sub> )	≥ 99.5 %
Color (APHA)	≤ 10
Residue after Evaporation	≤ 4 ppm
Solubility in H <sub>2</sub> O	Passes Test
Water (H <sub>2</sub> O)(by Karl Fischer titrn)	≤ 0.05 %
Acidity (μeq/g)	≤ 0.2
Alkalinity (μeq/g)	≤ 0.1
Chloride (Cl)	≤ 0.1 ppm
Phosphate (PO <sub>4</sub> )	≤ 0.3 ppm
Trace Impurities – Aluminum (Al)	≤ 50.0 ppb
Arsenic and Antimony (as As)	≤ 10.0 ppb
Trace Impurities – Barium (Ba)	≤ 20.0 ppb
Trace Impurities – Beryllium (Be)	≤ 100.0 ppb
Trace Impurities – Bismuth (Bi)	≤ 100.0 ppb
Trace Impurities – Boron (B)	≤ 10.0 ppb
Trace Impurities – Cadmium (Cd)	≤ 20.0 ppb
Trace Impurities – Calcium (Ca)	≤ 50.0 ppb
Trace Impurities – Chromium (Cr)	≤ 20.0 ppb
Trace Impurities – Cobalt (Co)	≤ 20 ppb
Trace Impurities – Copper (Cu)	≤ 10.0 ppb
Trace Impurities – Gallium (Ga)	≤ 50 ppb
Trace Impurities – Germanium (Ge)	≤ 50.0 ppb
Trace Impurities – Gold (Au)	≤ 20 ppb
Heavy Metals (as Pb)	≤ 200.0 ppb
Trace Impurities – Iron (Fe)	≤ 50.0 ppb
Trace Impurities – Lead (Pb)	≤ 20.0 ppb
Trace Impurities – Lithium (Li)	≤ 50.0 ppb
Trace Impurities – Magnesium (Mg)	≤ 20 ppb

>>> Continued on page 2 >>>

Test	Specification
Trace Impurities – Manganese (Mn)	≤ 15.0 ppb
Trace Impurities – Molybdenum (Mo)	≤ 100.0 ppb
Trace Impurities – Nickel (Ni)	≤ 10.0 ppb
Trace Impurities – Niobium (Nb)	≤ 100.0 ppb
Trace Impurities – Potassium (K)	≤ 100 ppb
Trace Impurities – Silicon (Si)	≤ 50 ppb
Trace Impurities – Silver (Ag)	≤ 20.0 ppb
Trace Impurities – Sodium (Na)	≤ 100.0 ppb
Trace Impurities – Strontium (Sr)	≤ 20.0 ppb
Trace Impurities – Tantalum (Ta)	≤ 100.0 ppb
Trace Impurities – Thallium (Tl)	≤ 10.0 ppb
Trace Impurities – Tin (Sn)	≤ 100 ppb
Trace Impurities – Titanium (Ti)	≤ 20 ppb
Trace Impurities – Vanadium (V)	≤ 100.0 ppb
Trace Impurities – Zinc (Zn)	≤ 50 ppb
Trace Impurities – Zirconium (Zr)	≤ 100.0 ppb
Particle Count at point of fill – 0.5 µm and greater (Rion KS42AF)	≤ 150 par/ml
Particle Count at point of fill – 1.0 µm and greater (Rion KS42AF)	≤ 25 par/ml

>>> Continued on page 3 >>>

2-Propanol  
CMOS  
(iso-propyl alcohol)



Material No.: 9059-4S

---

Test

Specification

---

---

For Microelectronic Use

Packaging Site: Phillipsburg Mfg Ctr & DC

A handwritten signature in blue ink that reads 'Jamie Ethier'.

Jamie Ethier  
Vice President Global Quality

For questions on this Product Specification please contact Technical Services at 855.282.6867 or +1.610.386.1700  
Avantor Performance Materials, LLC

100 Matsonford Rd, Suite 200, Radnor, PA 19087. U.S.A. Phone 610.386.1700